



SUGGESTED PRINT SETS (1)			
Suggested print sets	unit	value	test method
extruder temp	C°	215-235	internal
plate temp	C°	cold to 45	internal
min. nozzle diameter	mm.	0,3	internal
fan	%	0-50	internal
print speed	mm/l°	10-20	internal
PROPERTY			
Physical			
Specific gravity	g/cm3	1,2	ISO 1183
Mechanical at 23°C / 50% rh			
Tensile strain	MPa	40	ISO 37
Charpy impact (23°C)	kJ/m ²	no break	ISO 179
Charpy impact (-30°C)	kJ/m ²	no break	ISO 179
Elongation at break	%	750	ISO 37
Compression set (70°C)	%	35	ISO 815
Abrasion loss	mm ³	42	ISO 4649
Hardness	sh/A	70	ISO 62

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .



ADDITIONAL INFORMATIONS

In General filaments made with Flexmark 7 (TPU) can be processed on conventional 3D printer using FDM / FFF technology.

Flexmark 7 (TPU) is a special polyurethane developed for 3D printing and to obtain best results we recommend pre drying the filaments at 70° for 2 h. Increase drying time for spools up 1 kg.

More than 3 hours can change melt flow index.

Don't leave the filament stopped inside the nozzle more than 20 min. If that down the temperature under 180°, better stop the thermal control.

(1) Suggested print set merely represent a recommendation for general use . Every printer necessity a specific set , nozzle temp, bed temp, etc .

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .